



Valona GR 7007 HC

DESCRIPTION

VALONA GR 7007 HC is a low viscosity, chlorine-free neat and honing oil.

APPLICATIONS

- **VALONA GR 7007 HC** is dedicated for grinding, honing to both ferrous and non-ferrous metals.

ADVANTAGES

This product is formulated from a hydrocracked base stock and provide many advantages:

- **Very good anti-wear and extreme pressure performances**
- Very good surface finish,
- Conferring low rugosity and high dimensional accuracy,
- Ensure that very high G factors can be achieved and the intervals between diamond finished lengthened.
- **Very little odor** due to its low aromatic compound content.
- **Improvement to operators' health** due to almost no carcinogenic compounds such as polycyclic aromatic hydrocarbons present in the oil.
- **Reduced oil mists and less product consumption** through evaporation, due to low levels of volatility.

- **Supreme product life** is ensured through increased oxidation stability.
- **Improved filtration ratio**, due to efficient degassing of the product.
- **Excellent compatibility with elastomers and paints.**

This lubricant used as recommended and for the application for which it has been designed does not present any particular risk. A material safety data sheet conforming to the regulations in use in the E.C. can be obtained from your local commercial advisor or downloaded at ms-sds.totalenergies.com

TECHNICAL DATA SHEET

V.01/2024

Valona GR 7007 HC



TYPICAL CHARACTERISTICS

Typical characteristics	Methods	Units	VALONA GR 7007 HC
Appearance	-	-	Clear liquid
Density at 15°C	ISO 3675	kg/m3	835
Kinematic viscosity at 40°C	ISO 3104	mm2/s	8
Open cup flash point	ISO 2592	°C	160

The characteristics shown in this table are typical values given for illustrative purposes.

This lubricant used as recommended and for the application for which it has been designed does not present any particular risk. A material safety data sheet conforming to the regulations in use in the E.C. can be obtained from your local commercial advisor or downloaded at ms-sds.totalenergies.com

TotalEnergies Lubrifiants

SA 552 006 454 RCS Nanterre - France

